

Polypropylene Impact Copolymer

Injection Molding

Product Description:

PP Copolymer 3400MN is a heterophasic natural colored high flow, medium impact resistance and nucleated grade produced by the latest Spheripol II

Technology with following features:

- Excellent processability.
- Good balance of Impact & Stiffness properties

Recommended Applications:

PP Impact Copolymer 3400MN is recommended for Injection Molding & Compounding applications like

- Industrial & Automotive components
- Appliances
- Thin Walled products
- Compounding

Typical Properties:

| Tested Properties | Test Method | UOM | Values* |
|--|-------------|--------------------|---------|
| Resin Properties | | | |
| Melt Flow Index (230 ^o C & 2.16 Kg) | ASTM D 1238 | gm/10 min | 40.0 |
| Density @ 23 ^o C | ASTM D 1505 | gm/cm ³ | 0.90 |
| Mechanical Properties | | | |
| Tensile Strength @ Yield (50 mm/min) | ASTM D 638 | MPa | 26.0 |
| Elongation @ Yield (50 mm/min) | ASTM D 638 | % | 6.0 |
| Flexural Modulus (1.0 % Secant & at 1.3 mm/min) | ASTM D 790 | MPa | 1200 |
| Notched Izod Impact Strength @ 23 ^o C | ASTM D 256 | J/m | 60 |
| Thermal Properties | | | |
| Heat Deflection Temperature (0.46 N/m ²) | ASTM D 648 | ^o C | 105 |
| Vicat Softening Point (10 N) | ASTM D 1525 | ^o C | 147 |

* Typical values not to be construed as specification limits. Values may change without any prior notice.

* Mechanical properties tested on specimen molded as per ASTM D 4101 and conditioned as per ASTM D 618.

Recommended Processing Temperature: 170 – 230 °C

Packaging Information:

This material is packed and available in raffia bags with net content of 25.0 Kg only. The raffia bags used conforms to the minimum strength requirements of BIS, however, customer shall take due care while handling the bag. Prolonged exposure of these bags to sunlight may deteriorate the bag's performance and cause spillage and wastage. IOCL does not warranty loss of material due to poor material handling practices.

Regulatory Information:

PP Copolymer 3400MN shall meet the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water'. The grade and Additives incorporated in this grade shall meet the positive list of constituents as prescribed in IS 10909. The Grade and the additives incorporated in it will also comply with the FDA: CFR Title 21,177.1520, Olefin Polymers.

Prevent PP Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the Storage temperature should not exceed 50 °C. Non - compliance to these precautionary measures can lead to degradation of the product causing Color changes, Odor & inadequate product performance. It is advised to process PP material within 06 months after delivery.

Disclaimer: IOCL assumes no liability whatsoever in respect of application, processing or any use made of the aforementioned information or products, or any consequence thereof. No liability whatsoever shall attached to any of the IOCL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.



Registered Office Address →
G-9, Aliyavar Jung Marg,
Bandra (East), Mumbai – 400051
Maharashtra, India.

Contact Address →
Product Application and Development Center (PADC),
Near Panipat Naphtha Cracker Complex,
Village – Bajjattan, Panipat – 132140, Haryana, India

Contact Details →
Tel : +91-180-2526705, 2528651
Fax : +91-180-2528689
Web : <https://propel.indianoil.in>